EPOXY49 | MVB 49

100% SOLIDS MOISTURE VAPOR BARRIER (25 LBS MVER)

PART A
RESIN

PRODUCT: VAPOR BARRIER (100% SOLIDS)
FORMAT: 3-GALLON KIT (2×A + 1×B = 11.7 KG)

CONTENTS: PART A = 1 GAL (4.0 KG NET)
MIX RATIO: 2A : 1B BY VOLUME (2:1 WT)

1. SHOT BLAST / GRIND

Profile concrete to open-pore ICRI CSP 3. Suppresses up to 25 lbs MVER & 99% RH. Never acid-etch.

2. MIX 2A : 1B

Pre-stir Part A 1 min. Combine 2 Parts A + 1 Part B by volume. Drill blend 3 min @ 350 RPM.

3. FAST POUR NOW

RAPID 11–20 MIN POT LIFE! Pour entire batch onto slab immediately in ribbons — do NOT leave in bucket!

4. SEAL & RECOAT

Spread w/ 16-mil notched squeegee (100 sq ft/gal) & cross-roll pinhole-free. Recoat in 4–16 hrs.



WARNING

H315: Causes skin irritation. H317: May cause an allergic skin reaction. H319: Causes serious eye irritation. Wear nitrile gloves, safety goggles & adequate ventilation. Keep tightly sealed at 60°F–80°F.

FULL ASTM TDS & SDS
EPOXY49.COM

24-HR CHEMTREC
1-800-424-9300